



## 简介\Introduction

聚醚多元醇CHK-3602 是由含活性氢基团的化合物为起始剂，在催化剂作用下，与氧化乙烯和氧化丙烯开环聚合反应而成。本产品主要用于制备MDI体系胀气慢回弹块泡和模塑泡，相比CHE-3601，胀气感更足。也可用作超柔软泡沫的基础聚醚。


Polyether polyols CHK-3602 are copolymerized from the ring-opening of propylene oxide and ethylene oxide with active hydrogen compounds as initiator under the effect of the catalyst. The products are mainly used to prepare gas bearing slow resilience slabstock foam and molded foam of MDI system. They are more adequate with gas bearing compared with CHE-3601. And they can also be used as original polyether polyols for ultra-soft foam.

## 规格\Specifications


|                                |  |                                    |
|--------------------------------|--|------------------------------------|
| 外观\Apperance                   | 无悬浮物，无机械杂质的均匀黏稠液体<br>Uniform viscous liquid without mechanical impurities and suspended solids | 目测\Visual                          |
| 羟值\Hydroxyl Value<br>(mgKOH/g) | 33~37  | GB/T 12008.3-2009                  |
| 水含量\Water Content<br>(%)       | ≤0.05  | GB/T 22313-2008/<br>ISO 14897:2002 |
| 酸值\ Acid Value<br>(mgKOH/g)    | ≤0.08  | GB/T 12008.5-2010                  |
| 钾离子含量\ K <sup>+</sup> (mg/kg)  | ≤5   | GB/T 12008.4-2009                  |
| 色度\ Color (Pt/Co)              | ≤100   | GB/T 605-2006                      |
| 黏度\ Viscosity<br>mPa·s (25°C)  | 900~1400   | GB/T 12008.7-2010                  |



## 温度和黏度曲线\Curve of Viscosity vs Temperature



## 温度和密度曲线\Curve of Density vs Temperature



长华化学科技股份有限公司技术部

Technology Department of Changhua Chemical Technology Co.,Ltd.