



简介\Introduction

聚醚多元醇PEG-600是由含活性氢基团的化合物为起始剂，在碱金属催化剂作用下，与氧化乙烯开环聚合反应而成。本产品是无BHT、无胺的聚醚，具有低K⁺、Na⁺、低CPR等特性。


Polyether polyols PEG-600 are copolymerized from the ring-opening of ethylene oxide with active hydrogen compounds as initiator under the effect of the catalyst. The products are typical BHT-free and amine-free polyether polyols with the characteristics of low K⁺\Na⁺, low CPR, etc.

规格\Specifications


外观(25℃)\ Apperance	无悬浮物，无机械杂质的均匀黏稠液体 Uniform viscous liquid without mechanical impurities and suspended solids	目测\Visual
羟值\Hydroxyl Value (mgKOH/g)	180~195	GB/T 12008.3-2009
水含量\Water Content (%)	≤0.05	GB/T 22313-2008/ ISO 14897:2002
酸值\Acid Value (mgKOH/g)	≤0.08	GB/T 12008.5-2010
黏度\Viscosity mPa·s (25℃)	实测	GB/T 12008.7-2010
钾离子含量\K ⁺ (mg/kg)	≤2	GB/T 12008.4-2009
pH	5~7	GB/T 12008.2-2010 附录B
色度\Color (Pt-Co)	≤50	GB/T 605-2006
CPR	≤1.5	CH-ZB-JS-011-2019



温度和黏度曲线\Curve of Viscosity vs Temperature



温度和密度曲线\Curve of Density vs Temperature



长华化学科技股份有限公司技术部
Technology Department of Changhua Chemical Technology Co.,Ltd.